



碳元素(厦门)新材料有限公司

Carbon (Xiamen) New Materials Co., Ltd

基本信息 / Basic information

产品名称	name:	PA66-CF-BCF2
树脂类型	resin type:	聚酰胺-66 Nylon66
纤维类型	fiber type:	碳纤维 Carbon Fiber
纤维含量	fiber content:	20% 碳纤维 20% Carbon Fiber
颜色	color:	黑色 Black
材料特性	material properties:	无卤阻燃、导电、耐磨、耐热、抗疲劳，适用于充电桩壳体、动力电池包阻燃隔板及建筑行业应急照明灯具外壳等有防火需求的场景。 Halogen-free flame-retardant property, electrical conductivity, wear resistance, heat resistance, and fatigue resistance; it is suitable for housings for charging piles, flame-retardant separators for power battery packs, housings for emergency lighting fixtures in the construction industry, and other scenarios with fire protection requirements.

材料参数/Material Parameters

物理性能 Physical Properties	典型性能 Typical Characteristic	测试标准 Testing Standard
密度 Density	1.25 g/cm ³	ISO 1183
吸水率 Water Absorption	0.2-0.4 %	ISO 2008
成型收缩率 Molding Shrinkage	0.3-0.5 %	ISO 2001
机械性能 Mechanical Properties	典型性能 Typical Characteristic	测试标准 Testing Standard
拉伸模量 Tensile Modulus	18577 MPa	ISO 527
拉伸强度 Tensile Strength	163 MPa	ISO 527
拉伸伸长率 Tensile Elongation	2.8 %	ISO 527
弯曲强度 Flexural Strength	253 MPa	ISO 178
弯曲模量 Flexural Modulus	12175 MPa	ISO 178

此数据表格中的数值信息仅供参考，不承担任何法律责任，针对数值有疑问的地方，请联系我们。
website : www.carbonele.com 中文网站 : www.carbonele.cn



碳元素(厦门)新材料有限公司

Carbon (Xiamen) New Materials Co., Ltd

冲击性能 Impact Performance	典型性能 Typical Characteristic	测试标准 Testing Standard
悬臂梁缺口冲击强度 Izod Notched Impact Strength	11.4 KJ/m ²	ISO 179
悬臂梁无缺口冲击强度 Notched impact strength of cantilever beam	111.7 KJ/m ²	ISO 179
电性能 Electrical	典型性能 Typical Characteristic	测试标准 Testing Standard
表面电阻系数 Surface Resistivity	E4-E6 Ω	ISO 3915-2022
热性能 Thermal performance	典型性能 Typical Characteristic	测试标准 Testing Standard
热变形温度 Heat Deflection Temperature	255 °C	ISO 1634
熔融温度 Melting Point	240-280 °C	ISO 3146
燃烧性能 Combustion Performance	V-0 (2.0 mm)	UL 94
加工处理 Processing and Handling	典型性能 Typical Characteristic	测试标准 Testing Standard
注射压力 Injection Pressure	85-130 MPa	
熔体温度 Melt Temperature	240-280 °C	
模具温度 Mold Temperature	75-90 °C	
干燥温度 Drying Temperature	100-120 °C	
干燥时间 Drying Time	3-5 H	

此数据表格中的数值信息仅供参考，不承担任何法律责任，针对数值有疑问的地方，请联系我们。
website : www.carbonele.com 中文网站 : www.carbonele.cn



材料简介/Material Introduction

碳纤维是一种高性能增强的复合材料，具有耐高温、抗摩擦、导电、导热及耐腐蚀等特性，

碳纤维的性能取决于其原料及制造过程，生产的产品适用于注塑，压缩和挤出成型的应用。

碳纤维增强复合材料可用航空航天、汽车、体育、建筑、机械、电子电器等领域的应用还将不断扩大。

Carbon fiber is a high-performance reinforced composite material with characteristics of high temperature resistance, anti-friction, electricity conductivity, heat conductivity and corrosion processes, resistance. The performance of carbon fiber depends on its raw materials and manufacturing and the products are suitable for applications of injection molding, compression molding, and extrusion molding. The application of carbon fiber reinforced composite materials in aerospace, automobile, sports, machinery, electronics and electrical equipment and other fields will continue to expand.

注意事项/Precautions and Considerations

使用本材料时，应注意避免过度加热或过度剪切，以免损坏材料的性能，选择适合碳纤维的注塑机，压力、注射速度、模具温度等参数应根据碳纤维材料的特性进行调整，碳纤维材料特性，注塑机在使用过程中可能会受到较大的磨损，腐蚀。因此，应定期对机台进行维护保养、确保机台的正常运行和使用寿命。

When using this material, it is important to avoid excessive heating or shearing to prevent damage to the material's properties. It is necessary to select an injection molding machine suitable for carbon fiber, and the parameters such as pressure, injection speed, and mold temperature should be adjusted to the characteristics of the carbon fiber material. The carbon fiber material has unique properties, and according to the injection molding machine may suffer from significant wear and corrosion during use. Therefore, regular maintenance of the machine should be conducted to ensure its normal operation and service life.

此数据表格中的数值信息仅供参考，不承担任何法律责任，针对数值有疑问的地方，请联系我们。